


TECHNICAL FEATURES

TECNODECK® ONE



TECNODECK® ONE

DENSITY EN ISO 1183-1 (g/cm ³)	1,33
WEIGHT (Kg/ml)	2,38 (+/- 5%)
INFLUENCE OF MOISTURE, EN 317	
WATER ABSORPTION (%)	0,50
SWELLING THICKNESS (%)	0,20
CONTENT AND RELEASE OF DANGEROUS SUBSTANCES	Contains no dangerous substances
BENDING STRENGTH (N/mm ²)	21,0
BENDING STRENGTH EN 789 (N/mm ²) - characteristic value.	17,0
MODULUS OF ELASTICITY IN BENDING EN 310 (N/mm ²) (Distance between supports 500 mm)	3500
IMPACT STRENGTH EN 477	
+23°C/1KG	100 cm (9,8J) (no rupture)
-10°C/1 KG	100 cm (9,8J) (no rupture)
THERMAL EXPANSION COEFFICIENT (K ⁻¹)	41,4x10 ⁻⁶
ISO 11359 [-40°C, 80°C]	
SLIP RESISTANCE DIN 4843, PART 100 (Barefoot, dry and wet)	Pass the specifications
SLIP RESISTANCE DIN 51130:2014, SLIP ANGLE 33,9°	R12
FIRE BEHAVIOUR	Not tested

NOTE:

The Tecnodeck® profiles dimensions have a tolerance of ± 1mm.

These features are only for information purposes, and the manufacturer may change them without previous notice.

v.01/2022